

BMA Nitrocellulose Sealer Special

Code: BMA-SSN270

Color: Clear

PROPERTIES

A nitrocellulose based sealer, formulated with excellent filling and levelling properties. It is especially designed for sealing a wide range of wood substrates and for woodworking industries where transparency for related products is required.

RECOMMENDED USES

BMA NC Sealer Special could be used for:

- ✓ Wood furniture
- ✓ Chairs and frames
- ✓ Wooden floors
- ✓ Bars and kitchens bench tops

PERFORMANCE BENEFITS

- ✓ Sealing, sanding and filling properties
- ✓ Quick drying
- ✓ Very high viscosity

CHARACTERISTIC PHYSICO-CHEMICAL DATA

| Test | Norms | Results |
|---|------------|---------------------|
| Total solids, by weight | ASTM D2369 | 46% |
| Specific Gravity (g/cm ³) | ASTM D1475 | 1 |
| Spreading Rate at 35µm DFT ⁽¹⁾ | - | 8 m ² /L |

¹⁾ DFT: Dry Film Thickness

APPLICATION GUIDE

Surface Preparation

Before applying BMA NC Sealer Special, all necessary pretreatment must be done. Surface should be clean, dry and free of all contaminants (oils, agents, dust, dirt, etc...) in order to avoid the risk of surface failing.

Wooden surface:

For previously painted wooden surface, remove paint residues using a scraper in order to avoid the flaking of the new coating in case it is not compatible with the old one. Sand and smooth the surface then clean it well and remove the sanding dust. Let the surface dry before any primer or sealer application.

For new wood, sand the surface and all the edges lightly until smoothing. Apply an insulator (PU Milesi) for oily wooden substrate. Then, use NC Putty BMA-PUN to close off, patch and fill all surface imperfections (cracks, holes, pores, etc...). Clean the substrate and let it dry then make sure that the moisture content does not exceed 10%. Sand until smoothing using a sanding paper with a 300 grit size. Clean it well before any coating application.

Thinning

If thinning is required, 10 to 15% (for brush or roller application) and 150 to 200% (for air spraying application) of BMA Thinner Super, Thinner Extra or Thinner 050 could be used in order to obtain the required viscosity.

Application

BMA NC Sealer Special should be applied in a well-ventilated area where the humidity does not exceed 85% and the temperature not less than 5°C.

Before any application, the surface must be sufficiently dried in order to obtain the desired result. Since the system is clear, apply BMA Wood Stain BMA-STs then 2 to 3 layers of BMA Sealer, depending on the porosity of the wood.

The application could be done using a brush, roller or an air spraying system. Sanding must be done after 3 hours and overcoating after 3 hours as well at 25°C.

To note that BMA SSN270 is unsuitable to be immersed in water.

Drying Time

Surface (Touch) Dry: 10 minutes

Through Dry: 30 minutes

Dry to sand: 45 minutes
Dry to over coat: 3 hours

AVAILABLE PACKAGING

1 US Gallon = 3.786 L; 5 US Gallons Pail = 18.9 L

SHELF LIFE

BMA NC Sealer Special should be stored in closed and undamaged containers in a well-ventilated area where the temperature varies between 10 and 35°C. The product must be kept away from direct exposure to sunlight or any heat or flame source.

Under these conditions, the shelf life of BMA SSN270 will be 2 years. After this period, the products quality is subjected to re-inspection. Proper handling is essential to maintain good quality.

HEALTH & SAFETY

Before using this product please consult our Safety Data Sheet (SDS) for complete information on Hazards Identification, First-Aid and Fire-Fighting Measures, Accidental Release Measures, Handling and Storage, Exposure Control and Personal Protection, Stability and Reactivity, Toxicological Information, and Transport Information.

QUALITY ASSURANCE

BMA Commercial & Industrial s.a.l is a holder of the ISO 9001:2015 and OHSAS 18001:2007 certificates, which guarantees that all operations are conducted in compliance with International Standards.



TDS.23 - Edition #: 1

IMPORTANT: The statements, technical information and recommendations contained herein are believed to be accurate. Since the conditions and methods of use of the product and of the information referred to herein are beyond our control, BMA Commercial & Industrial s.a.l expressly disclaims any and all liability as to any results obtained or arising from any use of the product or reliance on such information.