

BMA PRIMOPOXY FOR CONCRETE

Code: BMA-CPE

Code of the hardener: BMA-HPE800

Color: Catalogue Colors

PROPERTIES

A two component Solvent Based Epoxy, with good hardness and chemical resistance, used as a primer to provide chemical protection and mechanical strength against environmental conditions. It is applied on any type of indoor and outdoor well prepared concrete walls and floors substrates.

RECOMMENDED USES

BMA Primopoxy is used for:

- ✓ Concrete walls and floors
- ✓ Chemical, water and power plants
- ✓ Marine applications and swimming pools
- ✓ Warehouses and parkings

PERFORMANCE BENEFITS

- ✓ Good heat, salt water and chemical resistance
- ✓ Good corrosion protection from environmental impact
- ✓ Good abrasion and impact resistance
- ✓ Good adhesion to the surface
- ✓ Withstanding heavy duties
- ✓ Good non-slipping properties
- ✓ High durability

CHARACTERISTIC PHYSICO-CHEMICAL DATA

Material Analysis of **Primopoxy for concrete (Part A)** cross linked with **Hardener BMA-HPE800 (Part B): (A+B):**

Tests	Norms	Results
Total Solids, by weight	ASTM D1259	74%
Consistency, at 25°C (Part A)	ASTM D562	30 Poises
Specific Gravity (g/cm ³)	ASTM D1475	1.47
Total Volatile Organic Compound (VOC)	ASTM D3960	387.6 g/L
Spreading Rate at 40 µm DFT ⁽¹⁾	-	14.3 m ² /L
Recommended WFT ⁽²⁾ @10%	-	77 µm
Hardener Code	-	BMA-HPE800
Hardener Percentage	-	25%
Pot Life	-	2 hours

¹⁾ DFT: Dry Film Thickness

²⁾ WFT: Wet Film Thickness

APPLICATIONS GUIDE

Surface Preparation

Before applying BMA Primopoxy for Concrete, all necessary pretreatment must be done. Surface should be clean, dry and free of all contaminants (oils, agents, dust, dirt, etc...) in order to avoid the risk of surface failing.

Concrete substrate must be well prepared in order to avoid any coating defects.

For new surface, ensure that concrete is completely cured at least 30 days.

For both fresh and old concrete, decontamination is required to remove any dust, oil, grease, laitance, fatty acids or any additional contaminants. Acid etching is recommended

using Eksen Kimya Hydrochloric Acid Solution. Decontamination could be also done using detergent scrubbing, low pressure water cleaning, or steam.

After cleaning, fill and repair any surface irregularities (cracks, holes and pores) with the cementitious mixture.

Cementitious mixture preparation: first, prepare a SBR Solution by mixing BMA SBR with water (1:5 by volume). Then, add the SBR Solution to the cement and sand until reaching the desired cementitious mixture.

Allow concrete substrate to dry then check the moisture and the pH of the substrate. Ensure that the pH is between 6 and 9 since alkalinity can affect and destroy paint adhesion. For the moisture content, make sure that it does not exceed 4% (by weight). Otherwise, the concrete surface is not a good candidate for painting.

Mixing

Mix thoroughly 25% by volume of the hardener BMA-HPE800 with BMA Primopoxy. Apply the mixture within its pot lifetime (2 hours) at ambient temperature.

Thinning

If thinning is necessary, a maximum of 10- 15 % (for brush or roller application) and 15- 20% (for airless spraying system) of BMA Thinner Epoxy (BMA-THI130) could be added in order to obtain the required viscosity of the mixture.

Application

BMA Primopoxy should be applied in a well-ventilated area where the humidity does not exceed 85% and when the temperature varies between 5°C and 40°C.

The application must be done on a clean and dry surface using a brush, roller or airless spraying system within the pot life of the prepared mixture (4 hours). It is recommended to apply the first coat of BMA Primopoxy using a brush in order to avoid any formation of holes and fish eyes on the surface. The product should not be exposed to heavy mechanical stress before being full cured.

Overcoating could be done after 6 hours using for example BMA Enamopoxy for concrete BMA-CEE cross-linked with 25% of its hardener BMA-HPE800.

The substrate should be dried for 2 days before light foot traffic, 5 days before heavy foot traffic and 10 days before vehicle traffic.

Drying Time

Surface (touch) dry: 2 hours
Dry to over coat: 10 - 24 hours
Dry to handle: 24 – 48 hours

AVAILABLE PACKAGING

Gallon Kit = 4L + 1L; Pail Kit = 20L + 5L

SHELF LIFE

BMA Primopoxy for concrete should be stored in closed and undamaged containers in a well-ventilated area where the temperature varies between 5°C and 35°C and away from any source of heat or freezing. Direct exposure to sunlight should be avoided.

Under these conditions, the shelf life of BMA Primopoxy for concrete will be 1 year and of its hardener 1 year.

After these periods, the products are subjected to re-inspection. Proper handling is essential to maintain good quality.

HEALTH & SAFETY

Before using this product, please consult our Safety Data Sheet (SDS) for complete information on Hazards Identification, First-Aid and Fire-Fighting Measures, Accidental Release Measures, Handling and Storage, Exposure Control and Personal Protection, Stability and Reactivity, Toxicological Information, and Transport Information.

QUALITY ASSURANCE

BMA Commercial & Industrial s.a.l is a holder of the ISO 9001:2015 and ISO 45001:2018 certificates, which guarantees that all operations are conducted in compliance with International Standards.

TDS.14 - Edition #: 3

IMPORTANT: The statements, technical information and recommendations contained herein are believed to be accurate. Since the conditions and methods of use of the product and of the information referred to herein are beyond our control, BMA

Commercial & Industrial s.a.l expressly disclaims any and all liability as to any results obtained or arising from any use of the product or reliance on such information.