

BMA WB UNDERBODY COATING

Code: DIF-UBW

Color: Black

PROPERTIES

Water-based Underbody Coating is a premium copolymer coating, designed to protect the metal frames and underbody components of any type of vehicle, and prevent any corrosion damage to the metal. BMA Underbody Coating could be applied to a variety of substrates such that wood, foam, and plastic.

RECOMMENDED USES

BMA Underbody Coating could be used for:

- ✓ Concrete waterproofing insulator
- ✓ Protection of underbody components of automobiles, SUV trailers, utility bodies
- ✓ Wood

PERFORMANCE BENEFITS

- ✓ Quick-drying properties for early water and weather resistance
- ✓ Resistant to salt, alkalis, and moisture
- ✓ It protects against abrasion and corrosion by providing a durable plastic layer
- ✓ At higher film builds, it provides sound deadening and vibration dampening

CHARACTERISTIC PHYSICO-CHEMICAL DATA

Tests	Norms	Results
Total solids, by weight	ASTM D3960	55%
Specific Gravity (g/cm ³)	ASTM D1475	1.2
Consistency, at 25°C (Poise)	ASTM D562	50
Dry opacity; contrast ratio at 150µm	-	> 0.95
Spreading Rate at 35µm DFT ⁽¹⁾	-	13 m ² /L

¹⁾ DFT: Dry Film Thickness

APPLICATIONS GUIDE

Surface Preparation

Before applying BMA Underbody Coating, all necessary pretreatment must be done. Surface should be clean, dry and free of all contaminants (oils, agents, dust, dirt, etc...) in order to avoid the risk of surface failing.

Concrete surfaces:

Concrete substrate must be well prepared in order to avoid any coating defects.

For new surface, ensure that concrete is completely cured for at least 30 days.

For both fresh and old concrete, decontamination is required to remove any dust, oil, grease, laitance, fatty acids or any additional contaminants. This could be done using detergent scrubbing, low pressure water cleaning, or steam.

Allow concrete substrate to dry then check the moisture and the pH of the substrate. Ensure that the pH is between 6 and 9 since alkalinity can affect and destroy paint adhesion. For the moisture content, make sure that it does not exceed 4% (by weight). Otherwise, the concrete surface is not a good candidate for painting.

Thinning

For the first layer, use 25% of water and for the second one use 10 to 15% of water also for an application using a roller.

Application

BMA Underbody Coating should be applied in a well-ventilated area where the humidity does not exceed 80% and the temperature varies between 5°C and 40°C.

The application can be done with a roller on a clean and dry surface.

It is recommended to apply two layers sufficiently diluted in order to obtain maximum surface protection and insulation.

Drying Time

Surface (Touch) Dry: 5 hours
Through Dry: 24 hours

AVAILABLE PACKAGING

GAMBINI Pail = 17 L

SHELF LIFE

BMA Underbody Coating should be stored in closed and undamaged containers in a well-ventilated area where the temperature varies between 10 and 40°C. The product must be kept away from direct exposure to sunlight or any heat or flame source.

Under these conditions, the shelf life of BMA Underbody Coating will be 2 years. After this period, the product quality is subjected to re-inspection. Proper handling is essential to maintain good quality.

HEALTH & SAFETY

Before using this product please consult our Safety Data Sheet (SDS) for complete information on Hazards Identification, First-Aid and Fire-Fighting Measures, Accidental Release Measures, Handling and Storage, Exposure Control and Personal Protection, Stability and Reactivity, Toxicological Information, and Transport Information.

QUALITY ASSURANCE

BMA Commercial & Industrial s.a.l is a holder of the ISO 9001:2015 and ISO 45001:2018 certificates, which guarantees that all operations are conducted in compliance with International Standards.

TDS. 227 - Edition #: 1

IMPORTANT: The statements, technical information and recommendations contained herein are believed to be accurate. Since the conditions and methods of use of the product and of the information referred to herein are beyond our control, BMA Commercial & Industrial s.a.l expressly disclaims any and all liability as to any results obtained or arising from any use of the product or reliance on such information.