

SEALER Z

Code: 1BM-SNN210

Color: Clear

PROPERTIES

Sealer Z is formulated with excellent filling and levelling properties. It is especially designed for sealing a wide range of wood substrates and for woodworking industries where transparency for related products is required.

RECOMMENDED USES

Sealer Z could be used for:

- ✓ Wood furniture
- ✓ Chairs and frames
- ✓ Wooden floors
- ✓ Bars and kitchens bench tops

PERFORMANCE BENEFITS

- ✓ Sealing, sanding and filling properties
- ✓ Quick drying
- ✓ Very high viscosity

CHARACTERISTIC PHYSICO-CHEMICAL DATA

Test	Norms	Results
Total solids, by weight	ASTM D2369	44%
Specific Gravity (g/cm ³)	ASTM D1475	0.999
Spreading Rate at 35µm DFT ⁽¹⁾	-	11 m ² /L

¹⁾ DFT: Dry Film Thickness

APPLICATION GUIDE

Surface Preparation

Before applying Sealer Z, all necessary pretreatment must be done. Surface should be clean, dry and free of all contaminants (oils, agents, dust, dirt, etc...) in order to avoid the risk of surface failing.

Wooden surface:

For previously painted wooden surface, remove paint residues using a scraper in order to avoid the flaking of the new coating in case it is not compatible with the old one. Sand and smooth the surface then clean it well and remove the sanding dust. Let the surface dry before any primer or sealer application.

For new wood, sand the surface and all the edges lightly until smoothing. Apply an insulator for oily wooden substrate. Then, use NC Putty to close off, patch and fill all surface imperfections (cracks, holes, pores, etc...). Clean the substrate and let it dry then make sure that the moisture content does not exceed 10%. Sand until smoothing using a sanding paper with a 300-grit size. Clean it well before any coating application.

Thinning

Thinning is required, 10 to 15% (for brush or roller application) and 100 to 150% (for air spraying application) of Thinner Super, Thinner Extra or Thinner 050 could be used in order to obtain the required viscosity.

Application

Sealer Z should be applied in a well-ventilated area where the humidity does not exceed 85% and the temperature not less than 5°C.

Before any application, the surface must be sufficiently dried in order to obtain the desired result. Since the system is clear, apply Wood Stain then 2 to 3 layers of Sealer, depending on the porosity of the wood.

The application could be done using a brush, roller or an air spraying system. Sanding must be done after 3 hours and overcoating after 3 hours as well at 25°C.

Drying Time

Surface (Touch) Dry: 10 minutes

Dry to sand: 60 minutes

Dry to over coat: 3 hours

AVAILABLE PACKAGING

Kilo; US Gallon = 3.786 L; Pail = 20 L

SHELF LIFE

Sealer Z should be stored in closed and undamaged containers in a well-ventilated area where the temperature varies between 10 and 35°C. The product must be kept away from direct exposure to sunlight or any heat or flame source.

Under these conditions, the shelf life will be 2 years. After this period, the products quality is subjected to re-inspection. Proper handling is essential to maintain good quality.

HEALTH & SAFETY

Before using this product, please consult our Safety Data Sheet (SDS) for complete information on Hazards Identification, First-Aid and Fire-Fighting Measures, Accidental Release Measures, Handling and Storage, Exposure Control and Personal Protection, Stability and Reactivity, Toxicological Information, and Transport Information.

QUALITY ASSURANCE

BMA Commercial & Industrial s.a.l is a holder of the ISO 9001:2015 and ISO 45001:2018 certificates, which guarantees that all operations are conducted in compliance with International Standards.

TDS.264 - Edition #: 1

IMPORTANT: The statements, technical information and recommendations contained herein are believed to be accurate. Since the conditions and methods of use of the product and of the information referred to herein are beyond our control, BMA Commercial & Industrial s.a.l expressly disclaims any and all liability as to any results obtained or arising from any use of the product or reliance on such information.