

## BMA RUBBER EMULSION ANTI-BACTERIAL

Code :

BMA-APC	050-101
	102-118
	116

Color : Catalogue colors

### PROPERTIES

BMA Rubber Emulsion Anti-Bacterial BMA-APC is a vinyl acetate copolymer emulsion-based paint formulated with an excellent bacterial resistance for use on interior and exterior walls and ceilings. The anti-bacterial function extends the product's lifetime, minimizes the potential for cross contamination and reduces the risk of a bad odor. BMA-APC is washable and wipeable, providing a tough finish that is resistant to condensation, yellowing and most household stains. Its outstanding durability and hygienic property make it ideal for use in kitchens, bathrooms, hotels, hospitals, pharmaceuticals and public buildings.

### RECOMMENDED USES

BMA Rubber Emulsion Anti-Bacterial could be used for walls and ceilings on:

- ✓ Concrete
- ✓ Gypsum boards
- ✓ Plaster
- ✓ Primed wooden surfaces

### PERFORMANCE BENEFITS

- ✓ Extreme anti-bacterial activity
- ✓ Excellent dirt pick up resistance
- ✓ Inhibition of growth of bacterial odours
- ✓ Environmentally friendly
- ✓ A long-term performance
- ✓ Wipeable finish
- ✓ Flat finish
- ✓ Excellent coverage
- ✓ Easy washable

## CHARACTERISTIC PHYSICO-CHEMICAL DATA

Data related to the Rubber Emulsion Anti-bacterial BMA-APC, white color.

Tests	Norms	Results
Total solids, by weight	ASTM D2369	47.5%
Consistency, at 25°C	ASTM D562	119.5 KU
Specific Gravity (g/cm <sup>3</sup> )	ASTM D1475	1.25
Dry opacity; contrast ratio at 150µm (White)	-	> 0.96
Scrubability on 200µm WFT <sup>(1)</sup>	ASTM D2486	> 1200 cycles
Recommended WFT <sup>(1)</sup> at 20% Dilution	-	131.5 µm
Spreading Rate at 35µm DFT <sup>(2)</sup>	-	142.5 µm

<sup>1)</sup> WFT: Wet Film Thickness

<sup>2)</sup> DFT: Dry Film Thickness

## APPLICATIONS GUIDE

### Surface Preparation

Before applying BMA Rubber Emulsion Anti-Bacterial, all necessary pretreatment must be done. Surface should be clean, dry and free of all contaminants (oils, agents, dust, dirt, etc....) in order to avoid the risk of surface failing.

Concrete substrate must be well prepared in order to avoid any coating defects.

For new concrete surface, ensure that concrete is completely cured at least 30 days.

For both fresh and old concrete, decontamination is required to remove any dust, oil, grease, laitance, fatty acids or any additional contaminants. If needed, an ammonia solution could be used for a well cleaning.

### Priming

For light colors of BMA Rubber Emulsion Anti-Bacterial:

- Apply one coat of BMA Sealer White BMA-SEW151. Thinning could be done with 25 to 50% (for brush or roller application) and 35 to 75% of water (for air spraying application).

For dark colors of BMA Rubber Emulsion Anti-Bacterial:

- Apply one coat of BMA Sealer Clear BMA-SEW150. Thinning could be done with 30 to 60% (for brush or roller application) and 35 to 85% of water (for air spraying application).

## Thinning

Use 15 to 20% of water when applying using a brush or roller, and 20 to 25% of water for air spraying application.

## Application

BMA Rubber Emulsion Anti-Bacterial should be applied on a clean and dry surface in a well-ventilated area where the humidity does not exceed 75% and the paint temperature less than 10°C. Otherwise, more thinning will be required and extra water could affect the opacity and the sag resistance.

To obtain the best result, follow the below steps and apply the recommended systems:

### **For new surface application:**

- If the wall is in good conditions: apply one layer of BMA Extra Fill Putty BMA-PUW010 followed by two layers of BMA Ultra Fine Putty BMA-PUW020.
- If the wall is in bad conditions: apply two layers of BMA Extra Fill Putty BMA-PUW010 followed by one layer of BMA Ultra Fine Putty BMA-PUW020.
- A drying period of 12 hours is required between putty layers application.
- Rub the surface using a 150 – 180 grit rubbing paper.
- Clean the substrate with a soft broom or an air pressure system.
- Apply the designated BMA Sealer or BMA Water Based Undercoat (BMA-UNW) and let the surface dry for 12 hours as well.
- Apply one coat of BMA Rubber Emulsion Anti-Bacterial used as a checking layer in order to cover any remaining holes or uncovered areas by BMA Putty.
- Rub the checking layer after 24 hours with a 180 – 220 grit rubbing paper.
- Clean the substrate with a soft broom or an air pressure system.
- Finalize with two coats of BMA Rubber Emulsion Anti-Bacterial after thinning and using a brush, roller or air spraying system. Between the two layers application, rub the surface with a 220-grit rubber paper.

### **For pre-painted surface application:**

- Rub the surface with a fine waterproof abrasive paper followed by a well rinsing.
- Apply minimum two layers of water-based BMA Putty: at least one layer of BMA Extra Fill Putty BMA-PUW010 followed by at least one layer of BMA Ultra Fine Putty BMA-PUW020.
- Rub the surface after 12 hours using a 150 – 180 grit rubbing paper.

- Continue with the same steps recommended for a new surface application.
- If the pre-painted surface is in good condition, a direct application of BMA Rubber Emulsion Anti-Bacterial over a water-based paint could be done.

## Drying Time

Surface (Touch) Dry: 30 minutes

Dry to over coat: 4 hours

Through dry: 12 hours

## AVAILABLE PACKAGING

Gallon = 4L; Pail = 17L

## SHELF LIFE

BMA Rubber Emulsion Anti-Bacterial should be stored in undamaged and unopened containers in a well-ventilated area where the temperature varies between 10 and 35°C and far away from any heat or freezing source or a direct exposure to sunlight.

Under these conditions, the shelf life of BMA Rubber Emulsion Anti-Bacterial will be 18 months. After this period the product is subjected to re-inspection. Proper handling is essential to maintain good quality.

## HEALTH & SAFETY

Before using this product, please consult our Safety Data Sheet (SDS) for complete information on Hazards Identification, First-Aid and Fire-Fighting Measures, Accidental Release Measures, Handling and Storage, Exposure Control and Personal Protection, Stability and Reactivity, Toxicological Information, and Transport Information.

## QUALITY ASSURANCE

BMA Commercial & Industrial s.a.l is a holder of the ISO 9001:2015 and ISO 45001:2018 certificates, which guarantees that all operations are conducted in compliance with International Standards

TDS.62 - Edition #: 2

*IMPORTANT: The statements, technical information and recommendations contained herein are believed to be accurate. Since the conditions and methods of use of the product and of the information referred to herein are beyond our control, BMA Commercial & Industrial s.a.l expressly disclaims any and all liability as to any results obtained or arising from any use of the product or reliance on such information.*