

## BMA PU PRIMER

---

*Code: BMA-PPU*

*Code of its hardener: BMA-HPU300*

*Color: All catalogue colors*

### PROPERTIES

A two component polyurethane primer with fast drying, high durability, superior adhesion properties. It is designed to improve the bonding capacity for application on any steel or wooden substrates.

### RECOMMENDED USE

BMA Polyurethane Primer can be used for:

- ✓ Automotive vehicles and components
- ✓ Metallic or wooden furniture
- ✓ Doors and windows frames
- ✓ Industrial premises

### PERFORMANCE BENEFITS

- ✓ Quick drying
- ✓ Excellent durability
- ✓ Good adhesion and sealing capacity
- ✓ Good sanding properties
- ✓ Easy to apply

## CHARACTERISTIC PHYSICO-CHEMICAL DATA

Data corresponding to the PU Primer BMA-PPU cross-linked with its Hardener HPU300.

Tests	Norms	Results
Total solids, by weight	ASTM D2369	70.33%
Specific Gravity (g/cm <sup>3</sup> )	ASTM D1475	1.4 ± 0.1
Consistency, at 25°C	ASTM D562	100 KU
Spreading Rate at 35µm DFT <sup>(1)</sup>	-	15.3 m <sup>2</sup> /L
Recommended WFT <sup>(2)</sup> at 15% Dilution	-	78 µm
Recommended WFT <sup>(2)</sup> at 10% Dilution	-	72 µm
Total Volatile Organic Compound (VOC)	ASTM D3960	430.38 g/L
Hardener Code	-	BMA-HPU300
Hardener Percentage, by volume	-	50%
Pot Life	-	1 hour

<sup>1)</sup> DFT: Dry Film Thickness

<sup>2)</sup> WFT: Wet Film Thickness

## APPLICATIONS GUIDE

### Surface Preparation

Surface should be clean, dry and free of all contaminants (oils, dust, dirt, etc...) in order to avoid the risk of surface failing.

#### Treatment of wooden surfaces:

Moisture content in wood should not exceed 10%. A suitable filler should be applied to fill cracks and holes. Sand and smooth wooden surfaces. Milesi Polyurethane insulator (LQA 836 cross-linked with LNB 837) should be applied over the clean surface in order to isolate the wood before applying any primer.

#### Treatment of steel surfaces:

To obtain optimum performance, for metal surface, substrate must be cleaned by blast cleaning method. Acid and alkali rust scale should be neutralized by ammonia solution (5%). New steel must have surface profile to have key by means of mechanical or

chemical etching. Old aged coatings must be cleaned with water soluble oil emulsifiers and detergents and then rinsed with plenty of water.

## Mixing

Pour contents of BMA Polyurethane Primer into a larger container, add its corresponding hardener (HPU 300) and mix them thoroughly. The hardener percentage to the base component is 50% by volume.

## Thinning

If thinning is required, use 25 to 30% of BMA Thinner PU using a brush, roller or air spraying system.

## Application

BMA Polyurethane Primer should be applied in a ventilated area where the temperature varies between 5°C and 35°C and when relative humidity of the air does not exceed 65%. BMA Polyurethane Primer must be applied on a clean and dry surface. It could be applied by air spray, brush or roller.

## Drying Time

Surface (Touch) Dry: 15 minutes

Through Dry: 15 minutes

Dry to sand: 30 minutes

Dry to over coat: 12 hours

## AVAILABLE PACKAGING

1 US Gallon = 3.786 L; 5 US Gallons Pail = 18.9 L

## SHELF LIFE

BMA PU Primer should be stored in undamaged and unopened containers in a well-ventilated area where the temperature varies between 5°C and 35°C, far away from any heat or freezing source or a direct exposure to sunlight.

Under these conditions, BMA PU Primer has a shelf life of 2 years from date of manufacture and of its hardener it will be 1 year. After this period, the paint quality is subjected to re-inspection. Proper handling is essential to maintain good quality.

## HEALTH & SAFETY

Before using this product please consult our Safety Data Sheet (SDS) for complete information on Hazards Identification, First-Aid and Fire-Fighting Measures, Accidental Release Measures, Handling and Storage, Exposure Control and Personal Protection, Stability and Reactivity, Toxicological Information, and Transport Information.

## QUALITY ASSURANCE

BMA Commercial & Industrial s.a.l is a holder of the ISO 9001:2015 and ISO 45001:2018 certificates, which guarantees that all operations are conducted in compliance with International Standards.

TDS.90 - Edition #: 2

---

*IMPORTANT: The statements, technical information and recommendations contained herein are believed to be accurate. Since the conditions and methods of use of the product and of the information referred to herein are beyond our control, BMA Commercial & Industrial s.a.l expressly disclaims any and all liability as to any results obtained or arising from any use of the product or reliance on such information.*